

ALSAN RS Surfacers

Properties

ALSAN RS Surfacers is a filled, flexible methyl methacrylate-based surfacer.

Areas of application

ALSAN RS Surfacers is used to smooth out any unevenness in the substrates or to level out fleece overlaps in ALSAN RS Waterproofing and Coating Systems.

Colours

ALSAN RS Surfacers is available in the following standard colours:

Shade 7032 – Pebble grey

Packaging

| | |
|----------------|------------------------------|
| 10.00 kg | ALSAN RS Surfacers |
| <u>0.30 kg</u> | <u>Catalyst (3 x 0.1 kg)</u> |
| 10.30 kg | |

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

Mixing instructions

Stir or homogenise the surfacer before taking it out of the container. Then stir in the appropriate amount of catalyst for the amount of surfacer being used and mix thoroughly, ensuring that the material on the base and sides of the container is included.

Reaction times (at 20 °C)

| | |
|---|--------------------|
| Pot life | approx. 15 minutes |
| Rain-proof after | approx. 30 minutes |
| Can be walked on / next layer can be applied after | approx. 1 hours |
| Fully cured after | approx. 3 hours |

Consumption

Approx. 2,1 kg/m² per mm of layer thickness corresponds to approx. 2,1 kg/litre.

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 15 minutes) of the product.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.