

ALSAN RS 242 Mortar

Properties

ALSAN RS 242 Mortar is a highly-filled 2-component repair and levelling mortar based on methyl methacrylate resin and a formulated, activated filling mixture.

Areas of application

ALSAN RS 242 Mortar is used as a lean mortar or a gradient levelling mortar for subsequent ALSAN RS coating systems.

Colours

ALSAN RS Mortar is available in the following standard colours:

Asphalt black

Packaging

Summer formulation

10.00 kg	ALSAN RS 288 Finish
<u>0.20 kg</u>	<u>Catalyst (2 x 0.1 kg)</u>
10.20 kg	

Winter formulation

10.00 kg	ALSAN RS 288 Finish
<u>0.40 kg</u>	<u>Catalyst (4 x 0.1 kg)</u>
10.40 kg	

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

Mixing instructions

First stir the contents of the tub thoroughly, then add the catalyst while stirring at slow speed and mix for 2 minutes. Ensure that the material on the base and sides is mixed in.

Reaction times (at 20 °C)

Pot life	approx. 15 minutes
Rain-proof after	approx. 30 minutes
Can be walked on / next layer can be applied after	approx. 1 hours
Fully cured after	approx. 3 hours

Consumption

On even surfaces approx. 0.60 kg/m²

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 15 minutes) of the product.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.

Version 0901