

ALSAN RS Textured Coating

Properties

ALSAN RS Textured Coating is a flexibilised, filled methyl methacrylate-based surfacer with a grain guide.

Areas of application

ALSAN RS Textured Coating is used as a top coat on ALSAN RS 233 / 243 / 263 Self-Levelling Mortar GM on car park areas subjected to extreme mechanical stress, such as up and down ramps, cornering areas and busy road surfaces in interior and exterior applications.

Colours

ALSAN RS Textured Coating is available in the following standard colours:

Shade 7030 – Stone grey
Shade 7016 – Anthracite grey

Packaging

Summer formulation

15.00 kg	ALSAN RS Textured Coating (resin component)
0.20 kg	Catalyst (2 x 0.1 kg)
15.20 kg	

Winter formulation

15.00 kg	ALSAN RS Textured Coating (resin component)
0.40 kg	Catalyst (4 x 0.1 kg)
15.40 kg	

Storage

Can be stored unopened in a cool, dry place and protected against frost for approx. 6 months. Avoid direct sunlight on the packaging/containers, even on site.

Application conditions

The product can be applied at substrate and ambient temperatures between + 3 ° min. and + 35 ° max.

Mixing instructions

Stir the contents of the tub thoroughly, then add the catalyst while stirring at slow speed and mix for 2 minutes. Ensure that the material on the base and sides is mixed in. Ideally the entire material should be re-potted once.

Reaction times (at 20 °C)

Pot life	approx. 10 minutes
Rain-proof after	approx. 20 minutes
Can be walked on / next layer can be applied after	approx. 45 minutes
Fully cured after	approx. 2 hours

Consumption

On smooth substrates approx. 3.50 kg/m²

Cleaning the tools

When work is interrupted or completed the tools must be cleaned thoroughly with ALSAN RS Cleaning Agent within the pot life (approx. 10 minutes) of the product.

Information on risks and safety

See product safety data sheets.

The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for its suitability in any given case. We reserve the right to make changes in keeping with technical developments or improvements to our products.